

Stainless Steel Strips Standards Comparison Table

STS	USA	UNS	CHINA	EURONORM		RUSSIA	SWEDISH	JAPANESE
GRADE	AISI/ASTM	NO	GB	NO	NAME	GOST	SS	JIS
201	201	S20100	12Cr17Mn6Ni5N	1.4372	-	-	-	SUS 201
301	301	S30100	12Cr17Ni7	1.4310	X 12 CrNi 17 7	-	2331	SUS 301
303	303	S30300	1Cr18Ni9MoZr	1.4305	X 10 CrNiS 18 9	-	2346	SUS 303
304	304	S30400	06Cr18Ni9	1.4301	X 6 CrNi 18 10	08KH18N10 06KH18N11	2332	SUS 304
304L	304L	S30403	022Cr19Ni10	1.4307	X 3 CrNi 18 10	03KH18N11	2352	SUS 304L
316	316	S31600	0Cr17Ni12Mo2	1.4401	X 6 CrNiMo 17 12 2	-	2347	SUS 316
316L	316L	S31603	022Cr17Ni12Mo2	1.4404	X 3 CrNiMo 17 12 2	-	2348	SUS 316L
316Ti	316Ti	S31635	0Cr18Ni12Mo2Ti	1.4571	X 6 CrNiMoTi 17 12 2	08KH17N13M2T 10KH17N13M2T	2350	-
321	321	S32100	0Cr18Ni11Ti	1.4541/1.4878	X 6 CrNiTi 18 10	12KH18N10T	2337	SUS 321
347	347	S34709	0Cr18Ni11Nb	1.4550	X 6 CrNiNb 18 10	-	2338	SUS 347
309S	309S	S30908	0Cr23Ni13	1.4833	X 6 CrNi 22 13	20KH23N18	-	SUS 309S
310S	310S	S31008	06Cr25Ni20	1.4842	X 6 CrNi 25 20	20KH25N20S2	2361	SUS 310S
416	416	S41600	Y1Cr13	1.4005	X12CrS13	-	2380	SUS 416
2205	2205	S32205/S31803	00Cr22Ni5Mo3N	1.4462	X2CrNiMoN22-5-3	02Ch22N5AM2	2377	SUS 329J3L
2507	2507	S32750	00Cr25Ni7Mo4N	1.4410	X 2 CrNiMoN 25-7-4	-	-	-
904L	904L	N08904	-	1.4539	-	-	-	-
254SMO	254SMO	S31254	-	1.4547	X1CrNiMoCuN20-18-7	-	2378	-
253MA	253MA	S30815	-	1.4835	X9CrNiSiNCe21-11-2	-	2368	-
17-4PH/630	17-4PH/630	S17400	0Cr17Ni4Cu4Nb	1.4542	X5CrNiCuNb16-4	05Ch16N4D2B	-	SUS630